



Products:

IRON-FACE - FF-150HSCR-MO

High Strength Laminated Facer Film featuring Virtually Zero Stretch and Shrink and Zero Light transmission

- Scrim re-enforced METPET facer film.
- Heavy duty scrim reinforced tear resistant design.
- 2 Ply High Strength lamination
- Tensile @ break MD 22,000 PSI ASTM D 882.
- Tensile @ break TD 34,000 PSI ASTM D 882.
- Tensile Strength MD 37 Lb/In-Width ASTM D 882.
- Tensile Strength TD 36 Lb/In-Width ASTM D 882.
- COF .52-.60 ASTM D 1894.
- Tear MD 1015 Grams ASTM D 1922.
- Tear TD 1355 Grams.
- Puncture 47 lbs ASTM E 154
- Density .984 Grams/cc ASTM D 1505.
- Opacity 99.9% (zero light transmission).
- Thermal Shrinkage MD < 2% (5 min @ 266 deg F - air oven).
- Thermal Shrinkage TD < 1% (5 min @ 266 deg F - air oven).
- Widths up to 120".
- Flood Coat colors available upon request
- Printing any color up 4 colors



Proudly Made in the USA!

We Build It Smarter, Stronger...BETTER!

Colorado Facility

4699 Nautilus Court, Suite 402 / Boulder, CO 80302
p: 303.530.1748 / **f:** 303.530.1788
e: sales@flatiron-films.com / **w:** flatiron-films.com

Maryland Facility

9630 Gerwig Lane / Columbia, MD 21046
tf: 877.276.3456 (FILM) / **p:** 410.381.3456 (FILM) / **f:** 410.381.3459
e: info@flatiron-films.com / **w:** flatiron-films.com