



Products:

IRON-FACE - FF-400C4-WM®

***High Strength Laminated Facer Film featuring
Virtually Zero Stretch and Shrink and Zero Light Transmission***

- 4.5 mil 2 ply METPET/Coex/Cross linked blended Polyolefin film
- 2 Ply 6 layer laminated film
- Tensile strength MD 62 Lb/In-Width ASTM D 882
- Tensile strength TD 60 Lb/In-Width ASTM D 882
- COF .52 - .6 ASTM D 1894
- Tear MD 2,250 grams ASTM D 1922
- Tear TD 3,850 grams ASTM D 1922
- Dart Impact 1620 grams ASTM 1709
- Puncture 58 lbs ASTM E 154
- Density .952 grams/cm³
- Corona treated to 42+ dyne/cm²
- Opacity 99.9% (zero light transmission)
- Thermal shrinkage MD < 2% (5 min 266° air Oven)
- Thermal shrinkage TD < 1.5% (5 min 266° air Oven)
- Current width capacity 120"
- Standard colors White, Black, Blue with color matching capability (Pantone)
- Printing any color up 4 colors.



Proudly Made in the USA!

We Build It Smarter, Stronger...BETTER!

Colorado Facility

4699 Nautilus Court, Suite 402 / Boulder, CO 80302
p: 303.530.1748 / **f:** 303.530.1788
e: sales@flatiron-films.com / **w:** flatiron-films.com

Maryland Facility

9630 Gerwig Lane / Columbia, MD 21046
tf: 877.276.3456 (FILM) / **p:** 410.381.3456 (FILM) / **f:** 410.381.3459
e: info@flatiron-films.com / **w:** flatiron-films.com